# Ve-PB1-4902-en/ (01.01.2022)

## ift-Nachweis



### **Classification Report**

Number	21-004738-PR39 (NW-K05-02040609-en-02)		
Owner	Sika Schweiz AG Tüffenwies 16 8048 Zürich Switzerland		
Product	One component canned foam (OCF)		
Designation	Sika Boom®-531 Multiposition		
Details	Material polyurethane foam Application foam gun Density approx.16 kg/m³ (manufacturer's information) Colour beige Test state foamed with oversize, cut flush / cut to size after curing / conditioning		
Result	Decision rule: For the evaluation of conformity, the measurement uncertainty was not taken into account.		

	Characteristics	Result of the test
© if Rosenhein	Air permeability in new condition according to EN 12114	$a < 0.1 \text{ m}^3/[(\text{m h (daPa})^{2/3}]]$ Joint width $w = 20 \text{ mm}$ , Joint depth $d = 70 \text{ mm}$
© If Rosemblin	Sound reduction of joints according to EN ISO 717-1 (and EN ISO 10140-1)	$[Rs,w (C; C_{tr}) \ge 61 (-2;-4) dB]$ Joint width $w = 20 \text{ mm}$ , Joint depth $d = 100 \text{ mm}$
an Brown ham	Thermal conductivity according to EN 17333-5	$\lambda_{10} = 0.039 \text{ W/(m K)}$ Insulation board 270 x 270 x 30 mm <sup>3</sup>
© In Rosenheim	Water vapour resistance factor according to EN ISO 12572 – Climate set A	$\mu_{0/50} = 19$ Insulation cylinder t = 94 mm, d = 70 mm

**ift** Rosenheim 29.11.2023

Wolfgang Jehl, Dipl.-Ing. (FH)
Deputy Head of Testing Department
Building Component Testing

info@ift-rosenheim.de www.ift-rosenheim.de

Martin Heßler, Dipl.-Ing. (FH)
Project Engineer
Building Component Testing

Basis \*)

EN 12114 : 2000 EN ISO 717-1 : 2020 EN ISO 10140-1 : 2021 EN 17333-5 : 2020 EN ISO 12572 : 2016

\*) and the equivalent national versions (e.g. DIN EN)

ift-Nachweis: 21-004738-PR13 (NW-K05-02040609-en-03)

replaces ift-Nachweis: 21-004738-PR39 (NW-K05-02040609-en-01)

ift Product certification QM 360 contract no. 188 9026567 dated 02.09.2022

#### Representation



#### Instructions for use

The results obtained can be used as evidence in accordance with the above basis.

#### Validity

There is no time limit. When using this document the upto-dateness of above basis and the conformity of the product have to be observed.

The data and results given relate solely to the tested/described specimen. This test/evaluation does not allow any statement to be made on further characteristics of the present structure regarding performance and quality.

#### Notes on publication

The ift-Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

Identity-Check



 $\frac{www.ift\text{-}rosenheim.de/ift\text{-}geprueft}{\text{ID: CC3-79DC7}}$ 



